CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No. TC- 5648

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 07/09/2018

Lab ID	:	**CP-2018-09-04-02**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to CC roads and drains at Muneshwaranagara in Bagalagunte in Ward no.14
Agency	:	Sri. DR. Ramesh Babu, No.1884/7, 6th 'A' Block, Rajajinagara, 2nd Stage, Bengaluru-560010
Customer's Reference	:	EE/DD/WO/395/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	04-09-2018
Sample ID No	:	2018-09-04-02 /01
Customer ID	:	CC PAVEMENT
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M40 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	07/09/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	CC PAVEMENT	M40	31/08/2018	07/09/2018	149.96 X 149.41 X 149.89	22406	8.006	766.3	34.2	34.3
2	CC PAVEMENT	M40	31/08/2018	07/09/2018	151.97 X 150.60 X 149.03	22887	8.254	803.3	35.1	
3	CC PAVEMENT	M40	31/08/2018	07/09/2018	150.63 X 149.21 X 151.77	22475	8.217	757.4	33.7	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No. : TC- 9548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-09-04-02** **Date: 28/09/2018**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to CC roads and drains at Muneshwaranagara in Bagalagunte in Ward no.14
Agency	:	Sri. DR. Ramesh Babu, No.1884/7, 6th 'A' Block, Rajajinagara, 2nd Stage, Bengaluru-560010.
Customer's Reference	:	EE/DD/WO/395/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	04-09-2018
Sample ID No	:	2018-09-04-02 /02
Customer ID	:	CC PAVEMENT
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M40 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	28/09/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	CC PAVEMENT	M40	31/08/2018	28/09/2018	149.57 X 151.11 X 150.13	22601	8.388	996.7	44.1	43.7
2	CC PAVEMENT	M40	31/08/2018	28/09/2018	150.87 X 150.77 X 150.49	22747	7.995	982.7	43.2	
3	CC PAVEMENT	M40	31/08/2018	28/09/2018	150.76 X 150.73 X 151.01	22723	8.109	995.3	43.8	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No. : TC- 5548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Date: 07/09/2018

Lab ID	:	**CP-2018-09-04-02**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to CC roads and drains at Muneshwaranagara in Bagalagunte in Ward no.14
Agency	:	Sri. DR. Ramesh Babu, No.1884/7, 6th 'A' Block, Rajajinagara, 2nd Stage, Bengaluru-560010.
Customer's Reference	:	EE/DD/WO/395/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	04-09-2018
Sample ID No	:	2018-09-04-02 /01
Customer ID	:	CC PAVEMENT
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M40 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	07/09/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	CC PAVEMENT	M40	31/08/2018	07/09/2018	151.46 X 149.79 X 149.92	22687	8.047	775.9	34.2	33.6
2	CC PAVEMENT	M40	31/08/2018	07/09/2018	150.78 X 149.77 X 151.49	22582	8.230	763.3	33.8	
3	CC PAVEMENT	M40	31/08/2018	07/09/2018	151.59 X 151.25 X 151.94	22928	8.126	754.3	32.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No. : TC-954

Format No: CPTT/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-09-04-02** **Date: 28/09/2018**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to CC roads and drains at Muneshwaranagara in Bagalagunte in Ward no.14
Agency	:	Sri. DR. Ramesh Babu, No.1884/7, 6th 'A' Block, Rajajinagara, 2nd Stage, Bengaluru-560010.
Customer's Reference	:	EE/DD/WO/395/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	04-09-2018
Sample ID No	:	2018-09-04-02 /02
Customer ID	:	CC PAVEMENT
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M40 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 28/09/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	CC PAVEMENT	M40	31/08/2018	28/09/2018	151.89 X 150.35 X 151.56	22836	7.977	993.4	43.5	44.7
2	CC PAVEMENT	M40	31/08/2018	28/09/2018	149.43 X 149.64 X 149.55	22360	8.286	990.5	44.3	
3	CC PAVEMENT	M40	31/08/2018	28/09/2018	150.23 X 151.15 X 151.81	22706	8.241	1049.0	46.2	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date.....

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner